



ERS-White Flashing Mastic SB

P/N: 005-0045

For Professional Use Only



PRODUCT DESCRIPTION:

ERS-White Flashing Mastic SB is a heavy bodied, trowel grade adhesive. It is butyl based and asbestos free, with excellent adhesion to most roofing substrates. ERS-White Flashing Mastic SB stays flexible throughout its service life, ensuring good adhesion and unbroken contact to uneven surfaces. This results in a watertight bond even under conditions of normal roof movement. Also available in black with comparable properties.

RECOMMENDED USES:

ERS-White Flashing Mastic SB can be used to bond Hypalon or Elvaloy based membranes to mineral or smooth surface APP or SBS membranes. It also bonds ERS-7000 EPDM or ERS-8000-FB to approved bituminous, masonry or metal substrates and is suitable as a strip-in mastic.

ADVANTAGES:

- Easy application.
- Compatible with tar and asphalt bitumens.
- Contains no asphalt.
- Excellent weathering characteristics.
- Used as a repair material or adhesive with white single ply membranes; any excess application blends at seams and edges.
- Available in white or black.

INSTALLATION:

Surface Preparation: Surface must be clean and dry. Remove as much old embedded aggregate as possible. Prime aged surfaces with ERS-301 or ERS water-based primer.

Application: Using a roof or masonry trowel, apply ERS-White Flashing Mastic SB to the surface in a monolithic film. Allow material to flash for a minimum of 15 minutes on days warmer than 70°F and 30 – 45 minutes when temperatures are cooler than 70°F. Place flashing membrane into the still tacky ERS-White Flashing Mastic SB and work smooth with hand or roller pressure. ERS-White Flashing Mastic SB cannot be sprayed.

Clean Up: Clean with Xylene.

STORAGE LIFE:

One (1) year from date of shipment when stored in unopened, original container.

PACKAGING:

ERS-White Flashing Mastic SB is available in 5 gallon (18.9 liter) pails.

PRECAUTIONS:

ERS-White Flashing Mastic SB cannot be sprayed.

PHYSICAL PROPERTIES:

Property	Value	Test Method
Asbestos Content	0%	EPA 600/R-93/116
Viscosity @ 77°F	400,000 – 600,000 cps	ASTM D 2196
Density	9.1 – 9.3 lbs/gal.	ASTM D 1475
Flash Point	80°F	ASTM D 93
Solids by Weight (Non-volatile Matter)	73%	ASTM D 1353
Accelerating Aging	2000 hrs. – no signs of deterioration of film	ASTM D 4586
Elongation, min.	1000%	ASTM D 412
Recovery from 500% Elongation, min.	500%	ASTM D 412
Volatile Organic Compounds	Less than 300 g/L	ASTM D 3960
Flexibility	Flexible at -40°F, no cracking	ASTM D 3111

Ecology Roof Systems®

Corporate Offices

9821 Olde Eight Road, Unit F, Northfield, OH 44067

PHONE: 330-467-4220 FAX: 330-467-4225

www.ecologyroof.com

REGIONAL OFFICES LOCATED ACROSS THE U.S.

To the best of our knowledge, all technical data contained herein is true and accurate as of the date of issuance and subject to change without prior notice. User must contact Ecology Roof Systems to verify correctness before specifying or ordering. We guarantee our products to conform to the quality control standards established by Ecology Roof Systems. We assume no responsibility for coverage, performance or injuries resulting from use. Liability, if any is limited to replacement of the product. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND IS MADE BY ECOLOGY ROOF SYSTEMS, EXPRESSED OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.